



MASTER ADDITIVES SDN BHD (895227-A)

No. 1&3, Jalan Biola Satu 33/1A,

Elite Industrial Park, Seksyen 33,

40460 Shah Alam, Selangor

Contact : + 603 - 51224182 Fax: + 603 – 51224184

www.master-additives.com

TECHNICAL DATA

MA – B20

COMPOSITION : *Alkylphenol Formaldehyde resin*

PROPERTIES

TYPICAL

Appearance	Dark Yellowish Pastilles
Specific Gravity, g/cm ³	1.07
Softening Point, °C	135
Storage Stability	At least 2 years under normal conditions.
Packaging	25kg PE bag

APPLICATION

MA-B20 improves the building tack of synthetic rubber compounds. It has outstanding short- and long-term tackifying effects.

Unlike standard tackifiers, MA-B20 shows its strength in aged tack improvement at relatively low dosage levels; between 3 and 5 phr.

Recommended Dosage:

2 – 5 phr